WAXES FOR PRODUCING PRINTING INKS

Patent number:

WO0164799

Publication date:

2001-09-07

Inventor:

SCHMALZL MANFRED (DE); SLUITER GABRIELE (DE)

Applicant:

CLARIANT GMBH (DE); SCHMALZL MANFRED (DE);

SLUITER GABRIELE (DE)

Classification:

- international:

C09D11/02; C09D11/12; C09D123/04; C09D123/10; C09D191/06; C09D191/08; C08L27/18; C08L77/00; C08L91/06; C08L91/08; C09D11/02; C09D11/12; C09D123/00; C09D191/00; C08L27/00; C08L77/00;

C08L91/00; (IPC1-7): C09D11/02

- european:

C09D11/02B; C09D11/12; C09D123/04; C09D123/10;

C09D191/06; C09D191/08

Application number: WO2001EP01667 20010215

Priority number(s): DE20001009754 20000301; DE20001063424 20001220

Also published as:

D F

US2006009542 (A EP1272575 (B1)

Cited documents:

EP0890619 US5643984

EP0324077 DE4403478 US5591796

more >>

Report a data error he

Abstract of WO0164799

The invention relates to the use of mixtures for producing printing inks. Said mixtures consist of: a) a homopolymerizate or copolymerizate of C2-C18- alpha -olefins, which are produced by means of metallocene catalysis, and of decomposing waxes, which are prepared from polyolefins of longer chain lengths produced by means of metallocene catalysis, with one or more additional additives selected from the group comprised of: b) polytetrafluoroethylene having a molecular weight (Mn) ranging from 30,000 t 2,000,000 g/mol; c) a thermoplastic PTFE having a molecular weight (Mn) ranging from 500,000 to 10,000,000 g/mol whose particle size ranges from 1-100 mu m; d) amide waxes produced by reacting ammonia or ethylene diamine with saturated and unsaturated fatty acids; e) montan waxes including acid and ester waxes whose carboxylic acid has a carbon chain length ranging from C22 to C36; f) natural vegetable waxes; g) conversion products of sorbite (sorbitol) with saturated and/or unsaturated fatty acid and/or montan acids; h) synthetic hydrocarbons; i) paraffins and microcrystalline waxes which accrue during the refinery of petroleum; i) polar polyolefin waxes produced by oxidizing ethylene homopolymer and copolymer waxes or propylene homopolymer and copolymer waxes or by the grafting thereof to maleic anhydride; k) polyamides whose particle sizes range from 1-100 mu m; l) polyolefins, such as polyethylene, polypropylene or their copolymers of a high or low density having molecular weights (Mn) ranging from 10,000 to 1,000,000 g/mol whose particle sizes range from 1-100 mu m, and; m) agents which, in general, reduce the surface tension of liquids (wetting agents).

Data supplied from the esp@cenet database - Worldwide